Version number 2.1 (replaces version 2.0)

Printing date 13.03.2023



SECTION 1: Identification of the substance/mixture and of the company/ undertaking

- · 1.1 Product identifier
- · Trade name: KTM RACING 4T SAE 20W/60
- **1.2 Relevant identified uses of the substance or mixture and uses advised against** No further relevant information available.
- Application of the substance / the mixture Engine oil Only for proper handling.
- · 1.3 Details of the supplier of the safety data sheet

· Manufacturer/Supplier:

MOTOREX AG Bern–Zürich–Strasse 31, Postfach CH–4901 Langenthal Tel. +41 (0)62 919 75 75 www.motorex.com

· Further information obtainable from: msds@motorex.com

· 1.4 Emergency telephone number:

In case of a medical emergency following exposure to a chemical, the public should call NHS Direct in England or Wales 0845 46 47 or NHS 24 in Scotland 08454 24 24 24 (UK only).

SECTION 2: Hazards identification

· 2.1 Classification of the substance or mixture

· Classification according to Regulation (EC) No 1272/2008

Aquatic Chronic 3 H412 Harmful to aquatic life with long lasting effects.

- · 2.2 Label elements
- · Labelling according to Regulation (EC) No 1272/2008
- The product is classified and labelled according to the GB CLP regulation.
- · Hazard pictograms Void
- · Signal word Void
- · Hazard statements

H412 Harmful to aquatic life with long lasting effects.

Precautionary statements

P101 If medical advice is needed, have product container or label at hand.

P102 Keep out of reach of children.

P103 Read carefully and follow all instructions.

P273 Avoid release to the environment.

P501 Dispose of contents/container in accordance with local/regional/national/international regulations.

· Additional information:

Contains maleic anhydride, Reaction products of benzenesulfonic acid, mono-C20-24 (even)-secalkyl derivs. Para-, calcium salts. May produce an allergic reaction.

- 2.3 Other hazards
- · Results of PBT and vPvB assessment
- · PBT: Not applicable.
- · vPvB: Not applicable.

SECTION 3: Composition/information on ingredients

· 3.2 Mixtures

· Description: Mixture of substances listed below with nonhazardous additions.

(Contd. on page 2)





Printing date 13.03.2023

Trade name: KTM RACING 4T SAE 20W/60

		(Contd. of page
Dangerous components:		
CAS: 64742-54-7 EINECS: 265-157-1 Index number: 649-467-00-8 Reg.nr.: 01-2119484627-25	Distillates (petroleum), hydrotreated heavy paraffinic Asp. Tox. 1, H304	2.5-7.5%
	Mineral oils (mixture) Asp. Tox. 1, H304	≥2.5-≤7.5%
CAS: 84605-29-8 EINECS: 283-392-8 Reg.nr.: 01-2119493626-26	Phosphorodithioic acid, mixed O,O-bis (1,3- diethylbutyl and iso-Pr)esters, zinc salts Eye Dam. 1, H318; Aquatic Chronic 2, H411; Skin Irrit. 2, H315 Specific concentration limits: Eye Dam. 1; H318:C ≥ 12.5 % Eye Irrit. 2; H319: 12.5 % ≤ C < 12.5 %	≥0.25-<2.5%
EC number: 947-519-7	Reaction products of benzenesulfonic acid, mono-C20-24 (even)-sec-alkyl derivs. Para-, calcium salts Skin Sens. 1B, H317	0.1-0.25%
CAS: 121158-58-5 EC number: 310-154-3 Index number: 604-092-00-9 Reg.nr.: 01-2119513207-49	phenol, dodecyl-, branched Repr. 1A, H360F; Skin Corr. 1C, H314; Eye Dam. 1, H318; Aquatic Acute 1, H400 (M=10); Aquatic Chronic 1, H410 (M=10)	≥0.0025-<0.025
CAS: 108-31-6 EINECS: 203-571-6 Index number: 607-096-00-9	maleic anhydride Resp. Sens. 1, H334; STOT RE 1, H372; Skin Corr. 1B, H314; Eye Dam. 1, H318; Acute Tox. 4, H302; Skin Sens. 1A, H317 Specific concentration limit: Skin Sens. 1A; H317:C ≥ 0.001 %	≥0-<0.001%

· Additional information:

Note L: The classification as carcinogen does not apply because the mixture (or substance) contains less than 3% dimethyl sulfoxide extract (DMSO), measured according to IP 346. For the wording of the listed hazard phrases refer to section 16.

SECTION 4: First aid measures

- · 4.1 Description of first aid measures
- · After inhalation: Supply fresh air; consult doctor in case of complaints.
- · After skin contact:
- Remove residues with soap and water. Remove contaminated clothing immediately.
- · After eye contact:

Rinse opened eye for several minutes under running water. Consult a physician if irritation develops.

- After swallowing:
- Do not induce vomitting. Do not take in resorption stimulating agents.

Consult a physician who will decide on need and method of emptying the stomach.

- · 4.2 Most important symptoms and effects, both acute and delayed No further relevant information available.
- 4.3 Indication of any immediate medical attention and special treatment needed No further relevant information available.

(Contd. on page 3)

Oil of Switzerland Revision: 13.03.2023

Printing date 13.03.2023

Version number 2.1 (replaces version 2.0)

Trade name: KTM RACING 4T SAE 20W/60

(Contd. of page 2)

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- Suitable extinguishing agents: Use fire extinguishing methods suitable to surrounding conditions.
- · For safety reasons unsuitable extinguishing agents: DO NOT USE WATER JET
- 5.2 Special hazards arising from the substance or mixture
- In case of fire carbon, sulphur and phosphorus oxides can be formed.
- 5.3 Advice for firefighters
- · Protective equipment: No special measures required.

SECTION 6: Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Not required.
- · 6.2 Environmental precautions:

Do not allow product to reach sewage system or any water course. Inform respective authorities in case of seepage into water course or sewage system. Do not allow to enter sewers/ surface or ground water.

- 6.3 Methods and material for containment and cleaning up: Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust). Dispose contaminated material as waste according to item 13.
- 6.4 Reference to other sections No dangerous substances are released. See Section 7 for information on safe handling. See Section 8 for information on personal protection equipment. See Section 13 for disposal information.

SECTION 7: Handling and storage

· 7.1 Precautions for safe handling

Used oils (motor oils, gear oils, industrial oils) contain components causing skin cancer. Therefore, avoid skin contact by wearing protecting gloves. Carefully clean soiled parts of the skin with soap. • Information about fire - and explosion protection: Do not heat above flash point.

- \cdot 7.2 Conditions for safe storage, including any incompatibilities
- · Storage:

• Requirements to be met by storerooms and receptacles: No special requirements.

- Information about storage in one common storage facility: Not required.
- Further information about storage conditions:

The recommended storage temperature is (deg.C): ≤50°C Store containers closed and protect against rain, dust, heat and other atmospheric influences. • **Storage class:** 10

• 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

· 8.1 Control parameters

· Ingredients with limit values that require monitoring at the workplace:

108-31-6 maleic anhydride

WEL Short-term value: 3 mg/m³ Long-term value: 1 mg/m³ Sen

(Contd. on page 4)

GB

Printing date 13.03.2023

Version number 2.1 (replaces version 2.0)



Trade name: KTM RACING 4T SAE 20W/60

	Ls			
8460	5-29-8	8 Phosphorodithioic acid, mixed O,O- salts	-bis (1,3-diet	hylbutyl and iso-Pr)esters, zi
Oral		DNEL/general population/Systemic effect	sts/Long-term	0.24 mg/kg/24h (consumer)
Dermal Inhalative		DNEL / Workers / Systemic effects / Lon	g-term	12.1 mg/kg/24h (worker)
		DNEL/general population/Systemic effect	ts/Long-term	6.1 mg/kg/24h (consumer)
		DNEL / Workers / Systemic effects / Lon	g-term	8.31 mg/m3 (worker)
		DNEL/general population/Systemic effect	ts/Long-term	2.11 mg/m3 (consumer)
1211	58-58	-5 phenol, dodecyl-, branched		
Oral		DNEL/general population/Systemic effect	ts/Long-term	0.075 mg/kg/24h (consumer)
		DNEL/general pop/Systemic effects/acut	te-short term	1.26 mg/kg/24h (consumer)
Derm	nal	DNEL / Workers / Systemic effects / Lon	g-term	0.25 mg/kg/24h (worker)
		DNEL/Workers/Systemic effects/acute-s	hort term	166 mg/kg/24h (worker)
		DNEL/general population/Systemic effect	ts/Long-term	0.075 mg/kg/24h (consumer)
		DNEL/general pop/Systemic effects/acut	te-short term	50 mg/kg/24h (consumer)
Inhala	ative	DNEL/Workers/Systemic effects/acute-s	hort term	44.18 mg/m3 (worker)
		DNEL/general population/Systemic effect	ts/Long-term	0.79 mg/m3 (consumer)
		DNEL/general pop/Systemic effects/acut	te-short term	13.26 mg/m3 (consumer)
PNEC	Cs			
		8 Phosphorodithioic acid, mixed O,O·	bis (1.3-diet	hvlbutvl and iso-Pr)esters, zi
0.000		salts		
Oral	PNE	C / Predators / Secondary poisoning	10.67 mg/kg food (secondary poisonin (predators))	
	PNE	C / Aquatic organisms / Freshwater	0.004 mg/l (aquatic organisms)	
	PNE	C / Aquatic organisms / Marine water	0.0046 mg/l (aquatic organisms)	
	PNF		-	
		EC/Aquatic org/intermittent	U.U45 MG/I (a	aquatic organisms)
		cC/Aquatic org/intermittent ses(freshwater)	0.045 mg/i (8	
	relea	ses(freshwater) C/Aquatic organisms/Sewage treatment		aquatic organisms)
	relea PNE plant PNE	ses(freshwater) C/Aquatic organisms/Sewage treatment	100 mg/l (aq	aquatic organisms) uatic organisms)
	relea PNE plant PNE (fresh PNE	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment	100 mg/l (aq 0.02203 mg/	aquatic organisms) uatic organisms) (kg (aquatic organisms)
	relea PNE plant PNE (fresh PNE (mari	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment	100 mg/l (aq 0.02203 mg/ 0.002203 mg	aquatic organisms) uatic organisms) (kg (aquatic organisms)
	relea PNE plant PNE (fresh PNE (mari PNE	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment ine water)	100 mg/l (aq 0.02203 mg/ 0.002203 mg	aquatic organisms) uatic organisms) /kg (aquatic organisms) g/kg (aquatic organisms)
1211:	relea PNE plant PNE (fresl PNE (mari 58-58	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment ine water) C / Terrestrial organism / Soil	100 mg/l (aq 0.02203 mg/ 0.002203 mg 0.002206 mg/	aquatic organisms) uatic organisms) /kg (aquatic organisms) g/kg (aquatic organisms) /kg (terrestrial organisms)
1211: Oral	relea PNE plant PNE (fresh PNE (mari 58-58 PNE	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment ine water) C / Terrestrial organism / Soil I-5 phenol, dodecyl-, branched	100 mg/l (aq 0.02203 mg/ 0.002203 mg 0.00206 mg/ 4 mg/kg (predators))	aquatic organisms) uatic organisms) /kg (aquatic organisms) g/kg (aquatic organisms) /kg (terrestrial organisms)
1211 Oral	relea PNE plant PNE (fresh PNE (mari PNE 58-58 PNE	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment ine water) C / Terrestrial organism / Soil I-5 phenol, dodecyl-, branched C / Predators / Secondary poisoning	100 mg/l (aq 0.02203 mg/ 0.002203 mg/ 0.00206 mg/ 0.00206 mg/ 4 mg/kg f (predators)) 0.000074 mg	aquatic organisms) uatic organisms) /kg (aquatic organisms) g/kg (aquatic organisms) /kg (terrestrial organisms) food (secondary poisoni
1211 : Oral	relea PNE plant PNE (fresh PNE 58-58 PNE PNE PNE PNE	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment ine water) C / Terrestrial organism / Soil C - Sphenol, dodecyl-, branched C / Predators / Secondary poisoning C / Aquatic organisms / Freshwater	100 mg/l (aq 0.02203 mg/ 0.002203 mg/ 0.00206 mg/ 0.00206 mg/ 4 mg/kg (predators)) 0.000074 mg 0.000074 mg	aquatic organisms) uatic organisms) /kg (aquatic organisms) g/kg (aquatic organisms) /kg (terrestrial organisms) food (secondary poisoni g/l (aquatic organisms) ng/l (aquatic organisms)
1211: Oral	relea PNE plant PNE (fresh PNE 58-58 PNE PNE PNE PNE PNE	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment ine water) C / Terrestrial organism / Soil C / Terrestrial organism / Soil C / Predators / Secondary poisoning C / Aquatic organisms / Freshwater C / Aquatic organisms / Marine water E C / A q u a t i c o r g / i n t e r m i t t e n t ses(freshwater) C/Aquatic organisms/Sewage treatment	100 mg/l (aq 0.02203 mg/ 0.002203 mg/ 0.00206 mg/ 0.00206 mg/ 4 mg/kg (predators)) 0.000074 mg/ 0.000074 mg/	aquatic organisms) uatic organisms) /kg (aquatic organisms) g/kg (aquatic organisms) /kg (terrestrial organisms) food (secondary poisoni g/l (aquatic organisms) ng/l (aquatic organisms) l (aquatic organisms)
1211 Oral	relea PNE plant PNE (fresh PNE 58-58 PNE PNE PNE pNE plant PNE	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment ine water) C / Terrestrial organism / Soil C / Terrestrial organism / Soil C / Predators / Secondary poisoning C / Aquatic organisms / Freshwater C / Aquatic organisms / Marine water E C / A q u a t i c o r g / i n t e r m i t t e n t ses(freshwater) C/Aquatic organisms/Sewage treatment	100 mg/l (aq 0.02203 mg/ 0.002203 mg/ 0.00206 mg/ 0.00206 mg/ 4 mg/kg (predators)) 0.000074 mg 0.000074 mg/ 0.000074 mg/ 100 mg/l (aq	aquatic organisms) uatic organisms) /kg (aquatic organisms) g/kg (aquatic organisms) /kg (terrestrial organisms) food (secondary poisoni g/l (aquatic organisms) ng/l (aquatic organisms) 1 (aquatic organisms)
1211: Oral	relea PNE plant PNE (fresh PNE 58-58 PNE PNE PNE plant PNE (fresh PNE	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment ine water) C / Terrestrial organism / Soil F-5 phenol, dodecyl-, branched C / Predators / Secondary poisoning C / Aquatic organisms / Freshwater C / Aquatic organisms / Marine water E C / Aquatic organisms / Marine water E C / Aquatic organisms / Marine ter m ittent ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment	100 mg/l (aq 0.02203 mg/ 0.002203 mg/ 0.002203 mg/ 0.00206 mg/ 4 mg/kg f (predators)) 0.000074 mg/ 0.000074 mg/ 0.000037 mg/ 100 mg/l (aq 0.226 mg/kg	aquatic organisms) uatic organisms) /kg (aquatic organisms) g/kg (aquatic organisms) /kg (terrestrial organisms) food (secondary poisoni g/l (aquatic organisms) ng/l (aquatic organisms) (aquatic organisms) uatic organisms) (aquatic organisms)
1211: Oral	relea PNE plant PNE (fresh PNE 58-58 PNE PNE PNE plant PNE (fresh PNE (mari	ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment ine water) C / Terrestrial organism / Soil C / Terrestrial organism / Soil C / Terrestrial organism / Soil C / Aquatic organisms / Freshwater C / Aquatic organisms / Freshwater C / Aquatic organisms / Marine water E C / Aquatic organisms / Marine water E C / Aquatic organisms / Marine ter to ses(freshwater) C/Aquatic organisms/Sewage treatment /STP C / Aquatic organisms / Sediment hwater) C / Aquatic organisms / Sediment	100 mg/l (aq 0.02203 mg/ 0.002203 mg/ 0.002203 mg/ 0.00206 mg/ 4 mg/kg f (predators)) 0.000074 mg 0.000074 mg/ 0.000074 mg/ 100 mg/l (aq 0.226 mg/kg 0.0266 mg/kg	aquatic organisms) uatic organisms) /kg (aquatic organisms) g/kg (aquatic organisms) /kg (terrestrial organisms) food (secondary poisoning/l (aquatic organisms) ng/l (aquatic organisms) (aquatic organisms) uatic organisms) (aquatic organisms)

GB

Page 5/13

Safety data sheet according to 1907/2006/EC, Article 31



Printing date 13.03.2023

3 Version number 2.1 (replaces version 2.0)

Appropriate engineering controls No further data; see section 7. Individual protective and hygienic measures: Keep away from loodstuffs, beverages and feed. Wash hands before breaks and at the end of work. Do not inhale gases / furnes / aerosols. Respiratory protection: Not necessary if room is well-ventilated. Respiratory protection: The glove material has to be impermeable and resistant to the product/ the substance/ t preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of sev substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eyeface protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Fluid Colour: Dark yellow Codour: Characteristic Oddur threshold: Not determined. Helling point/freezing point: Not determined. Lower: Not determined. Pission emperature: Not determined. Pission emperature: Not determined. Pission is annelse, particular, anne		(Contd. of page
Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from loodstuffs, beverages and leed. Wash hands before breaks and at the end of work. Do not inhale gases / lumes / aerosols. Respiratory protection: Not necessary it room is well-ventilated. Respiratory protection if formation of aerosol or mist: use mask with filter type A2, A2/P2 or ABEK. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ t preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The eavet break through time has to be found out by the manufacturer of the protective gloves a has to be observed. SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Physical state Colour: Datk yellow Odour threshold: Not determined. Boiling point or initial boiling point and Boiling point or initial boiling point and Boiling point or explosion limit Lower: Not determined. Fiammability Not applicable. Lower: Not determined. Fiammability Not determined. Physical state Composition temperature: Not determined. Fiammability Lower: Not determined. Physical state Composition temperature: Not determined. Physical state Composition temperature: Not determined. Fiammability Lower: Not determined. Physical state Composition temperature: Not determined. Physical state Composition temperature: Not determined. Physical state Composition temperature: Not determined. Physical	8.2 Exposure controls	
General protective and hygienic measures: Keep away from toodstuffs, beverages and feed. Wash hands before breaks and at the end of work. Do not inhale gases / fumes / aerosols. Respiratory protection: Not necessary if room is well-ventilated. Respiratory protection if formation of aerosol or mist: use mask with filter type A2, A2/P2 or ABEK. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ to preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and to degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mair of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The esciption of aggles recommended during refilling Body protection Goggles recommended during refilling Body protection: Protective work clothing Selection on basic physical and chemical properties General Information Physical state Fluid Colour: Characteristic Odour threshold: Not determined. Boiling point orinitial boiling point and boiling point and b		
Keep away from foodstuffs, beverages and feed. Wash hands before breaks and at the end of work. Do not inhale gases / turnes / aerosols. Respiratory protection: Not necessary it room is well-ventilated. Respiratory protection if formation of aerosol or mist: use mask with filter type A2, A2/P2 or ABEK. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ t preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eyeface protection Goggles recommended during refilling Body protection : Protective work clothing SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Physical state Colour: Characteristic Odour threshold: Not determined. Boiling point or initial boiling point and boiling point or initial boiling point and boiling point or explosion limit Lower: Not determined. Flash point: Not determined. Physicolin temperature: Not determined. Physicolin temperature: Not determined. Solubility Not determined. Solubili		
Wash harids before breaks and at the end of work. Do not inhale gases / turnes / aerosols. Respiratory protection if formation of aerosol or mist: use mask with filter type A2, A2/P2 or ABEK. Hand protection if formation of aerosol or mist: use mask with filter type A2, A2/P2 or ABEK. Hand protection if formation of aerosol or mist: use mask with filter type A2, A2/P2 or ABEK. Hand protection if formation of aerosol or mist: use mask with filter type A2, A2/P2 or ABEK. Hand protection if the glove material on consideration of the penetration times, rates of diffusion and t degradation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Can not be calculated in advance and has therefor to be checked prior to the application. Selection Cancel and chemical properties Selection Gaggles recommended during refilling Body protection: Protective work clothing Selection: Solur: Characteristic Odour: Characteristic Odour: Characteristic		
Do not inhale gases / fumes / aerosols. Respiratory protection: Not necessary if room is well-ventilated. Respiratory protection if formation of aerosol or mist: use mask with filter type A2, A2/P2 or ABEK. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ t preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefe to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Fluid Colour: Characteristic Odour threshold: Not determined. Heiling point/freezing point: Undetermined. Flammability Not applicable. Lower and upper explosion limit Lower: Not determined. Flammability Lower: Not determined. Flammability Lower: Not determined. Flash point: Second upper explosion limit Lower: Not determined. Flash point: Not det		
Respiratory protection: Not necessary if room is well-ventilated. Respiratory protection The glove material has to be impermeable and resistant to the product/ the substance/ ti preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and ti degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection: Protective work clothing SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties Godour: Characteristic Odour: Characteristic Odour: Not determined. Boiling point or initial boiling point and boiling point and boiling range Undetermined. Flash point: Not determined. Lower: Not determined. Preprince Not determined. Previde state Sto 'C (DIN 51794) <		WOIK.
Not necessary if room is well-ventilated. Respiratory protection if formation of aerosol or mist: use mask with filter type A2, A2/P2 or ABEK. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ t preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of gloves Makerial Oxy ematerial The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. SecTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Meting point/reezing point: Undetermined. Meting point/reezing point: Undetermined. Meting point or initial boiling point and boiling point or initial boiling point and boiling range Flammability Lower: Not determined. Flammability Lower: Not determined. Pif Ash point: Not determined		
Respiratory protection if formation of aerosol or mist: use mask with filter type A2, A2/P2 or ABEK. Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ t preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eyeface protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Golour: Characteristic Odour threshold: Not determined. Boiling point or initial boiling point and boiling range Undetermined. Flash point: Lower: Not determined. Flash point: Pisto science: Not determined. Pisto science: Not d		
Hand protection The glove material has to be impermeable and resistant to the product/ the substance/ t preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be hecked prior to the application. Penetration time of glove material Panetration time of glove material Panetration time of glove material Benetration time of glove material Panetration time of glove material Benetration time of glove material Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Fluid Colour: Dark yellow Odour threshold: Not determined. Metting point or initial boiling point and Boiling range Lower: Not determined. Flash point: >200 °C Ignition temperature: Not determined. Physical state Not determined. Flash point:		or mist: use mask with filter type 12 12/02 or ADEK
The glove material has to be impermeable and resistant to the product/ the substance/ to preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Golour: Characteristic Odour threshold: Not determined. Boiling point or initial boiling point and Boiling point or initial boiling point and Boiling point explosion limit Lower: Not determined. Flammability Lower: Not determined. Flash point: Second point emperature: Not determined. Not determined. Not determined. Not determined. Not determined. Not determined. Solubility Water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log Walue) Not determined.		or mist. use mask with mer type Az, Az/1 Z OF ADEN.
Selection of the glove material on consideration of the penetration times, rates of diffusion and t degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Colour: Dark yellow Odour: Characteristic Odour threshold: Not determined. Melting point or initial boiling point and Boiling point or initial boiling point and Boiling point or initial boiling point and Boiling range Undetermined. Flammability Lower: Not determined. Flammability Not applicable. Lower: Not determined. Flash point: Physical state Consistency Metare point: Not determined. Flash point: Physical state Physical state Physical state Consistency Dynamic: Not determined. Solubility Water: Not determined. Solubility Water: Not determined. Physical state Not determined. Physical state N	The glove material has to be impermeab	le and resistant to the product/ the substance/ t
degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mar of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Physical state Fluid Colour: Dark yellow Odour threshold: Not determined. Melting point or initial boiling point and boiling onit or initial boiling point and boiling range Undetermined. Lower and upper explosion limit Not determined. Lowers: Not determined. PH Not determined. Ignition temperature: 255 °C (DIN 51794) Decomposition temperature: Not determined. PH Not determined. Viscosity: 168.3 mm2/s @ 40 °C Conosistency Not determined.	preparation.	
Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further mai of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material Can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Fluid Colour: Dark yellow Odour: Characteristic Odour: Not determined. Boiling point or initial boiling point and boiling point or initial boiling point and boiling range Undetermined. Flammability Not determined. Lower: Not determined. Ipper: Not determined. ph Not determined. Lower: Not determined. Pipers: Not determined. Lower and upper explosion limit >200 °C Lower: <		ation of the penetration times, rates of diffusion and t
The selection of the suitable gloves does not only depend on the material, but also on further main of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material an to be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Fluid Colour: Dark yellow Odour threshold: Not determined. Melting point/freezing point: Undetermined. Flammability Not applicable. Lower: Not determined. Flash point: 2200 °C Ignition temperature: 255 °C (DIN 51794) Decomposition temperature: Not determined. pH Not determined. Flash point: Not determined. pH Not determined. pH Not determined. pH		
of quality and varies from manufacturer to manufacturer. As the product is a preparation of seve substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Colour: Dark yellow Odour: Characteristic Odour threshold: Not determined. Boiling point or initial boiling point and boiling range Lower and upper explosion limit Lower: Not determined. Flash point: Securition temperature: Physical state Colour: Dark yellow Odour to restol with the manufacturer of the protective gloves a has to be observed. Securities and the protection of the applicable. Lower and upper explosion limit Lower: Not determined. Flash point: Securities and upper attrees Physical state Colour: Not determined. Flash point: Securities and upper attrees Physical state Physical state Physical of the applicable. Not determined. Flash point: Securities and upper attrees Securities and upper attrees Physical state Physical state	0	
substances, the resistance of the glove material can not be calculated in advance and has therefor to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Physical state Colour: Dark yellow Odour: Characteristic Odour threshold: Not determined. Boiling point or initial boiling point and boiling range Flammability Lower: Lower: Not determined. Flammability Not applicable. Lower: Not determined. Flammability Not determined. Flammability Not determined. Physics is the sploy of the protective gloves a Not determined. Physical state Fluid Colour: Dark yellow Odour: Characteristic Odour threshold: Not determined. Boiling point or initial boiling point and boiling range Undetermined. Flammability Not determined. Flash point: Not determined. Phy Not determined. Not determined. Phy Not determined. Phy Not determined. Phy Not determined. Phy Not determined. Phy Not determined. Phy Not determined. Not determined. Phy Not determined. Not determined. Phy Not determined. Phy Not determined. Phy Not determined. Phy Not determined. Phy Not determined. Phy Not determined. Phy Not determined. Phy Not determined. Phy Phy		
to be checked prior to the application. Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Colour: Dark yellow Odour: Coharacteristic Odour threshold: Not determined. Boiling point or initial boiling point and Boiling range Undetermined. Flammability Not applicable. Lower and upper explosion limit Lower: Not determined. Flash point: Secomposition temperature: Secomposition temperature: Secomposition temperature: Not determined. PH Not determined. Not miscible or difficult to mix. Partition coefficient n-octanol/water (log Not determined. PH Not		
Penetration time of glove material The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Physical state Fluid Colour: Dark yellow Odour threshold: Not determined. Melting point freezing point: Undetermined. Boiling point or initial boiling point and Undetermined. Flammability Not applicable. Lower: Not determined. Upper: Not determined. Flash point: >200 °C Upper: Not determined. pH Not determined.		erial can not be calculated in advance and has therefo
The exact break through time has to be found out by the manufacturer of the protective gloves a has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Physical state Fluid Colour: Dark yellow Odour: Characteristic Odour: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and boiling range Undetermined. Lower: Not determined. Lower: Not determined. Upper: Not determined. Flash point: >200 °C Ignition temperature: 255 °C (DIN 51794) Decomposition temperature: Not determined. pH Not determined. pH Not determined. pJnamic: Not determined. Solubility 168.3 mm²/s @ 40 °C Consistency Intermined. Solubility Not determined. Water: Not determined. Solubility Not		
has to be observed. Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Colour: Dark yellow Odour: Characteristic Odour threshold: Not determined. Melting point/reezing point: Undetermined. Flammability Not applicable. Lower: Not determined. Flash point: Sector Sect		ad and by the menufestimes of the sector of the
Eye/face protection Goggles recommended during refilling Body protection: Protective work clothing SECTION 9: Physical and chemical properties Seneral Information Physical state Fluid Colour: Dark yellow Odour: Characteristic Odour: Characteristic Odour: Undetermined. Melting point/freezing point: Undetermined. Boiling range Undetermined. Flammability Not applicable. Lower: Not determined. If and the point: >200 °C Ignition temperature: 255 °C (DIN 51794) Decomposition temperature: Not determined. pH Not determined. Viscosity: 168.3 mm²/s @ 40 °C Kinematic viscosity 168.3 mm²/s @ 40 °C Consistency Water: Dynamic: Not determined. Partition coefficient n-octanol/water (log value) Not determined. Not determined. Solubility water: Not determined. Partition coefficient n-octanol/water (log value) Not determined.		nd out by the manufacturer of the protective gloves a
Body protection: Protective work clothing SECTION 9: Physical and chemical properties General Information Physical state Colour: Dark yellow Odour threshold: Not determined. Melting point or initial boiling point and Boiling point or initial boiling point and Boiling range Undetermined. Lower and upper explosion limit Lower: Not determined. Flash point: >200 °C Ignition temperature: 255 °C (DIN 51794) Decomposition temperature: Not determined. pH Not determined. Viscosity: 168.3 mm2/s @ 40 °C Kinematic viscosity 168.3 mm2/s @ 40 °C Consistency Not determined. Dynamic: Not determined. Solubility Not determined. Water: Not determined. Partition coefficient n-octanol/water (log Not determined. Water: Not determined. Heat Capacity Not determined.		d de staar en Cillere
SECTION 9: Physical and chemical properties General Information Physical state Fluid Colour: Dark yellow Odour: Characteristic Odour: Characteristic Odour threshold: Not determined. Melting point/reezing point: Undetermined. Boiling point or initial boiling point and Boiling range boiling range Undetermined. Flammability Not applicable. Lower: Not determined. Upper: Not determined. Flash point: >200 °C Ignition temperature: 255 °C (DIN 51794) Decomposition temperature: Not determined. pH Not determined. Viscosity: 168.3 mm2/s @ 40 °C Kinematic viscosity 168.3 mm²/s @ 40 °C Consistency Not determined. Dynamic: Not determined. Solubility Not determined. water: Not determined. Partition coefficient n-octanol/water (log Not determined. Paulue) Not determined. Heat Capacity N		a during retilling
9.1 Information on basic physical and chemical properties General Information Physical state Fluid Colour: Dark yellow Odour: Characteristic Odour threshold: Not determined. Melting point/freezing point: Undetermined. Boiling point or initial boiling point and boiling range Undetermined. Flammability Not applicable. Lower and upper explosion limit Lower: Not determined. Flash point: >200 °C Ignition temperature: 255 °C (DIN 51794) Decomposition temperature: Not determined. pH Not determined. Viscosity: 168.3 mm2/s @ 40 °C Kinematic viscosity 168.3 mm2/s @ 40 °C Consistency Dynamic: Not determined. Solubility water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Heat Capacity	Body protection. Frotective work ciolning	
Physical stateFluidColour:Dark yellowOdour:CharacteristicOdour threshold:Not determined.Melting point/freezing point:Undetermined.Boiling point or initial boiling point andUndetermined.Boiling rangeUndetermined.FlammabilityNot applicable.Lower and upper explosion limitNot determined.Lower:Not determined.Ipper:Not determined.Flash point:>200 °CIgnition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.PHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm2/s @ 40 °CConsistencyNot determined.Pynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	-	
Colour:Dark yellowOdour:CharacteristicOdour threshold:Not determined.Melting point/freezing point:Undetermined.Boiling point or initial boiling point andUndetermined.Boiling rangeUndetermined.FlammabilityNot applicable.Lower and upper explosion limitLower:Lower:Not determined.Jpper:Not determined.Flash point:>200 °CIgnition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm²/s @ 40 °CConsistencyNot determined.Dynamic:Not determined.SolubilityNot determined.vater:Not determined.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che	
Odour:CharacteristicOdour threshold:Not determined.Melting point/freezing point:Undetermined.Boiling point or initial boiling point andUndetermined.boiling rangeUndetermined.FlammabilityNot applicable.Lower and upper explosion limitLower:Lower:Not determined.Jpper:Not determined.Jpmanic:Not determined.Jynamic:Not determined.SolubilityNot determined.water:Not determined.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information	emical properties
Odour threshold:Not determined.Melting point/freezing point:Undetermined.Boiling point or initial boiling point andUndetermined.boiling rangeUndetermined.FlammabilityNot applicable.Lower and upper explosion limitNot determined.Lower:Not determined.Upper:Not determined.Flash point:>200 °CIgnition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm2/s @ 40 °COot sistencyNot determined.Dynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state	emical properties
Melting point/freezing point:Undetermined.Boiling point or initial boiling point and boiling rangeUndetermined.FlammabilityNot applicable.Lower and upper explosion limitNot determined.Lower:Not determined.Upper:Not determined.Flash point:>200 °CIgnition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm2/s @ 40 °COpynamic:Not determined.SolubilityNot determined.water:Not determined.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state Colour:	emical properties Fluid Dark yellow
Boiling point or initial boiling point and boiling rangeUndetermined.FlammabilityNot applicable.Lower and upper explosion limitNot determined.Lower:Not determined.Upper:Not determined.Flash point:>200 °CIgnition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm²/s @ 40 °CConsistencyNot determined.Dynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour:	emical properties Fluid Dark yellow Characteristic
boiling rangeUndetermined.FlammabilityNot applicable.Lower and upper explosion limitNot determined.Lower:Not determined.Upper:Not determined.Flash point:>200 °CIgnition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm²/s @ 40 °CConsistencyNot determined.Dynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour:	emical properties Fluid Dark yellow Characteristic Not determined.
FlammabilityNot applicable.Lower and upper explosion limitNot determined.Lower:Not determined.Upper:Not determined.Flash point:>200 °CIgnition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm²/s @ 40 °CConsistencyNot determined.Dynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Value)Not determined.	-	emical properties Fluid Dark yellow Characteristic Not determined.
Lower:Not determined.Upper:Not determined.Flash point:>200 °CIgnition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm²/s @ 40 °CConsistencyNot determined.Dynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and	emical properties Fluid Dark yellow Characteristic Not determined. Undetermined.
Upper:Not determined.Flash point:>200 °CIgnition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm²/s @ 40 °CConsistencyNot determined.Dynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability	emical properties Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined.
Hash point:>200 °CIgnition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm²/s @ 40 °CConsistencyDynamic:Dynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range	Emical properties Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable.
Ignition temperature:255 °C (DIN 51794)Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm²/s @ 40 °CConsistencyNot determined.Dynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower:	Emical properties Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined.
Decomposition temperature:Not determined.pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm²/s @ 40 °CConsistencyNot determined.Dynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper:	Emical properties Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. Not determined.
pHNot determined.Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm2/s @ 40 °CConsistencyNot determined.Dynamic:Not determined.SolubilityNot miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point:	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. Not determined. >200 °C
Viscosity:168.3 mm2/s @ 40 °CKinematic viscosity168.3 mm2/s @ 40 °CConsistency168.3 mm2/s @ 40 °CDynamic:Not determined.SolubilityNot determined.water:Not miscible or difficult to mix.Partition coefficient n-octanol/water (log value)Not determined.Heat CapacityNot determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature:	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. Not determined. >200 °C 255 °C (DIN 51794)
Kinematic viscosity 168.3 mm²/s @ 40 °C Consistency Not determined. Dynamic: Not determined. Solubility Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Heat Capacity Not determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: Decomposition temperature:	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. >200 °C 255 °C (DIN 51794) Not determined.
Consistency Not determined. Dynamic: Not determined. Solubility Not miscible or difficult to mix. water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Heat Capacity Not determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: Decomposition temperature: pH	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. >200 °C 255 °C (DIN 51794) Not determined. Not determined. Not determined. Not determined.
Dynamic: Not determined. Solubility Not miscible or difficult to mix. water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Heat Capacity Not determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: Decomposition temperature: pH Viscosity:	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. >200 °C 255 °C (DIN 51794) Not determined. Not determined. Not determined. Not determined. Not determined. Not determined. 168.3 mm2/s @ 40 °C
Solubility water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Heat Capacity	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: Decomposition temperature: pH Viscosity: Kinematic viscosity	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. >200 °C 255 °C (DIN 51794) Not determined. Not determined. Not determined. Not determined. Not determined. Not determined. 168.3 mm2/s @ 40 °C
water: Not miscible or difficult to mix. Partition coefficient n-octanol/water (log value) Not determined. Heat Capacity Not determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: Decomposition temperature: pH Viscosity: Kinematic viscosity Consistency	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. >200 °C 255 °C (DIN 51794) Not determined. Not determined. Not determined. 168.3 mm2/s @ 40 °C 168.3 mm2/s @ 40 °C
Partition coefficient n-octanol/water (log value) Not determined. Heat Capacity	9.1 Information on basic physical and che General Information Physical state Colour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: pH Viscosity: Kinematic viscosity Consistency Dynamic:	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. >200 °C 255 °C (DIN 51794) Not determined. Not determined. Not determined. 168.3 mm2/s @ 40 °C 168.3 mm2/s @ 40 °C
value) Not determined. Heat Capacity	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: pH Viscosity: Kinematic viscosity Consistency Dynamic: Solubility	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. >200 °C 255 °C (DIN 51794) Not determined. Not determined. 168.3 mm2/s @ 40 °C 168.3 mm2/s @ 40 °C
Heat Capacity	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: pH Viscosity: Kinematic viscosity Consistency Dynamic: Solubility water:	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. >200 °C 255 °C (DIN 51794) Not determined. Not determined. 168.3 mm2/s @ 40 °C 168.3 mm2/s @ 40 °C
	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: Decomposition temperature: pH Viscosity: Kinematic viscosity Consistency Dynamic: Solubility water: Partition coefficient n-octanol/water (log	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. Not determined. >200 °C 255 °C (DIN 51794) Not determined. Not determined. 168.3 mm2/s @ 40 °C 168.3 mm2/s @ 40 °C Not determined. Not determined.
vapour pressure: Not determined.	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: Decomposition temperature: pH Viscosity: Kinematic viscosity Consistency Dynamic: Solubility water: Partition coefficient n-octanol/water (log value)	Fluid Dark yellow Characteristic Not determined. Undetermined. Undetermined. Not applicable. Not determined. Not determined. >200 °C 255 °C (DIN 51794) Not determined. Not determined. 168.3 mm2/s @ 40 °C 168.3 mm2/s @ 40 °C Not determined. Not determined.
	9.1 Information on basic physical and che General Information Physical state Colour: Odour: Odour threshold: Melting point/freezing point: Boiling point or initial boiling point and boiling range Flammability Lower and upper explosion limit Lower: Upper: Flash point: Ignition temperature: Decomposition temperature: pH Viscosity: Kinematic viscosity Consistency Dynamic: Solubility water: Partition coefficient n-octanol/water (log value) Heat Capacity	FluidDark yellowCharacteristicNot determined.Undetermined.Undetermined.Not applicable.Not determined.>200 °C255 °C (DIN 51794)Not determined.168.3 mm2/s @ 40 °C168.3 mm2/s @ 40 °CNot determined.Not determined.



Version number 2.1 (replaces version 2.0)



Trade name: KTM RACING 4T SAE 20W/60

	(Contd. of page
 Density and/or relative density 	
Density at 20 °C:	0.863 g/cm³ (ASTM D 4052)
Relative density	Not determined.
· Vapour density	Not determined.
9.2 Other information	
· Appearance:	
· Form:	Fluid
 Important information on protection of heat 	alth
and environment, and on safety.	
· Explosive properties:	Product does not present an explosion hazard.
Solvent separation test:	
VOC (EC)	0.00 %
Change in condition	
· Evaporation rate	Not determined.
· Information with regard to physical haz	ard
classes	
- Explosives	Void
Flammable gases	Void
Aerosols	Void
• Oxidising gases	Void
Gases under pressure	Void
Flammable liquids	Void
Flammable solids	Void
Self-reactive substances and mixtures	Void
· Pyrophoric liquids	Void
Pyrophoric solids	Void
Self-heating substances and mixtures	Void
Substances and mixtures, which emit	
flammable gases in contact with water	Void
· Oxidising liquids	Void
Oxidising solids	Void
· Organic peroxides	Void
Corrosive to metals	Void
Desensitised explosives	Void

SECTION 10: Stability and reactivity

- · 10.1 Reactivity No further relevant information available.
- 10.2 Chemical stability
- Thermal decomposition / conditions to be avoided: No decomposition if used according to specifications.
- 10.3 Possibility of hazardous reactions No dangerous reactions known.
- · 10.4 Conditions to avoid No further relevant information available.
- · 10.5 Incompatible materials: No further relevant information available.
- 10.6 Hazardous decomposition products: No dangerous decomposition products known.

SECTION 11: Toxicological information

- · 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008
- Acute toxicity Based on available data, the classification criteria are not met.
- · LD/LC50 values relevant for classification:

64742-54-7 Distillates (petroleum), hydrotreated heavy paraffinic

Oral LD50 5,000 mg/kg (rat)

(Contd. on page 7)

GB



GB

Printing date 13.03.2023

Version number 2.1 (replaces version 2.0)

Trade name: KTM RACING 4T SAE 20W/60

		(Contd. of pag
D (LOAEL	125 mg/kg/24h (rat)
Dermal	LD50	2,000-5,000 mg/kg (rabbit)
	NOAEL	150 mg/kg/24h (mouse)
		30-2,000 mg/kg/24h (rat)
		1,000 mg/kg/24h (rabbit)
	LOAEL	100 mg/kg/24h (mouse)
Inhalative	LC50 / 4h	
	NOEL	220 mg/m3 (rat)
	NOAEL	980 mg/m3 (rat)
84605-29-	·8 Phospho salts	orodithioic acid, mixed O,O-bis (1,3-diethylbutyl and iso-Pr)esters, zi
Oral	NOEL	40 mg/kg/24h (rat)
Ulai	NOEL	160 mg/kg/24h (rat)
Dermal	LD50	
		2,002 mg/kg (rat)
		2.3 mg/l (rat)
	•	, dodecyl-, branched
Oral	LD50	2,100-2,200 mg/kg (rat)
	NOEL	5-50 mg/kg/24h (rat)
_ /	NOAEL	60-100 mg/kg/24h (rat)
Dermal	LD50	15,000 mg/kg (rabbit)
	maleic anh	
Oral	LD50	400 mg/kg (rat)
Dermal	LD50	2,620 mg/kg (rabbit)
Serious e Respirato Germ cell Carcinogo Reproduc STOT-sin STOT-rep Aspiratio	ye damage ory or skin I mutagenie enicity Bas ctive toxici gle exposi peated expo n hazard B	tion Based on available data, the classification criteria are not met. e/irritation Based on available data, the classification criteria are not met. sensitisation Based on available data, the classification criteria are not me city Based on available data, the classification criteria are not met. sed on available data, the classification criteria are not met. ty Based on available data, the classification criteria are not met. ure Based on available data, the classification criteria are not met. Source Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Source Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met. Based on available data, the classification criteria are not met.
Endocrine	e disruptin	ng properties
121158-58	3-5 phenol,	, dodecyl-, branched Lis
SECTIO	N 10. Eo	ological information

· 12.1 Toxicity

64742-	-54-7 Distillates (petroleum), hydrotreated heavy paraffinic	
LL50	10,000 mg/l/96h (aquatic invertebrates)	
	100 mg/l/96h (fish)	
LL50	10,000 mg/l/72h (aquatic invertebrates)	
LL50	10,000 mg/l/48h (aquatic invertebrates)	
LL50	10,000 mg/l/24h (aquatic invertebrates)	
EL50	10,000 mg/l/48h (aquatic invertebrates)	
	(Contd. o	n page



Printing date 13.03.2023

Version number 2.1 (replaces version 2.0)

84605-2	9-8 Phosphorodithioic acid, mixed O,O-bis (1,3-diethylbutyl and iso-Pr)e salts	esters, z
LOEC	0.8 mg/l/21d (aquatic invertebrates)	
LC50	46 mg/l/96h (fish)	
EC50	10,000 mg/l/3h (microorganisms)	
LL50	4.5 mg/l/96h (fish)	
EL50	23 mg/l/48h (aquatic invertebrates)	
EL50	21-24 mg/l/72h (algae / cyanobacteria)	
NOEC	0.4-0.8 mg/l/21d (aquatic invertebrates)	
NOELR	1.8 mg/l/96h (fish)	
NOELR	10 mg/l/48h (aquatic invertebrates)	
Reactio calcium	n products of benzenesulfonic acid, mono-C20-24 (even)-sec-alkyl derivs. salts	Para-,
LC50	>1,000 mg/l/96h (Pimephales promelas)	
	>100 mg/l/96h (rainbow trout)	
EC50	>1,000 mg/l/96h (Alga)	
	58-5 phenol, dodecyl-, branched	
EC50	1,000 mg/l/3h (microorganisms)	
EC50	0.106 mg/l/24h (aquatic invertebrates)	
EC10	0.53-0.765 mg/l/72h (algae / cyanobacteria)	
EC50	0.15-0.765 mg/l/72h (algae / cyanobacteria)	
EC50	0.0079-0.0086 mg/l/21d (aquatic invertebrates)	
EC100	160 mg/l/48h (aquatic invertebrates)	
EC0	0.056 mg/l/48h (aquatic invertebrates)	
EC50	0.037-0.0927 mg/l/48h (aquatic invertebrates)	
EL50	40 mg/l/96h (fish)	
NOEC	0.0037 mg/l/21d (aquatic invertebrates)	
NOEC	0.07-0.442 mg/l/72h (algae / cyanobacteria)	
NOEC	0.011 mg/l/48h (aquatic invertebrates)	
NOEC	1,000 mg/l/3h (microorganisms)	
	25 mg/l/96h (fish)	
	0.012 mg/kg/28d (aquatic invertebrates)	
	sistence and degradability No further relevant information available.	
	accumulative potential	
	4-7 Distillates (petroleum), hydrotreated heavy paraffinic	
	coefficient >6 [] (log Kow) (Bioaccumulation)	
	9-8 Phosphorodithioic acid, mixed O,O-bis (1,3-diethylbutyl and iso-Pr)e salts	sters, z
	coefficient 0.56 [] (log Kow) (Bioaccumulation)	
	58-5 phenol, dodecyl-, branched	
	coefficient 6.1-7.14 [] (log Kow) (Bioaccumulation)	
Biodegra		
12.5 Re: PBT: No	bility in soil No further relevant information available. sults of PBT and vPvB assessment ot applicable.	
	lot applicable. docrine disrupting properties	
	INGINE GISTUUNUU UIUDEINES	

Version number 2.1 (replaces version 2.0)

Oil of Switzerlar Revision: 13.03.2023

Printing date 13.03.2023

Trade name: KTM RACING 4T SAE 20W/60

(Contd. of page 8)

12.7 Other adverse effects

Remark: Harmful to fish
 Additional ecological information:

· General notes:

Water hazard class 1 (according to Appendix 1 AwSV): slightly hazardous for water Do not allow undiluted product or large quantities of it to reach ground water, water course or sewage system.

Harmful to aquatic organisms

SECTION 13: Disposal considerations

· 13.1 Waste treatment methods

· Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

Contact waste processors for recycling information.

Return product and/or partially emptied container in original packaging to the point of sale or hand it over to a collection point for special waste.

· Uncleaned packaging:

Recommendation: Disposal must be made according to official regulations.

SECTION 14: Transport information

· 14.1 UN number or ID number · ADR/RID/ADN, ADN, IMDG, IATA	Void
· 14.2 UN proper shipping name · ADR/RID/ADN, ADN, IMDG, IATA	Void
· 14.3 Transport hazard class(es)	
· ADR/RID/ADN, ADN, IMDG, IATA · Class	Void
· 14.4 Packing group · ADR/RID/ADN, IMDG, IATA	Void
 14.5 Environmental hazards: Marine pollutant: 	No
 14.6 Special precautions for user 	Not applicable.
 14.7 Maritime transport in bulk according IMO instruments 	to Not applicable.
· UN "Model Regulation":	Void

SECTION 15: Regulatory information

- · 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients is listed.
- · 15.2 Chemical safety assessment: A Chemical Safety Assessment has been carried out.

(Contd. on page 10)



Printing date 13.03.2023

Version number 2.1 (replaces version 2.0)

Trade name: KTM RACING 4T SAE 20W/60

(Contd. of page 9)



Annex: Exposure scenario 1

· Short title of the exposure scenario

Industrial use of lubricants and greases in vehicles or machinery Sector of Use

SU3 Industrial uses: Uses of substances as such or in preparations at industrial sites

(Contd. on page 11)

GB



Printing date 13.03.2023

Version number 2.1 (replaces version 2.0)

(Contd. of page 10)
· Product category
PC16 Heat transfer fluids
PC17 Hydraulic fluids
PC24 Lubricants, greases, release products
Process category
PROC1 Chemical production or refinery in closed process without likelihood of exposure or
processes with equivalent containment conditions.
PROC2 Chemical production or refinery in closed continuous process with occasional controlled
exposure or processes with equivalent containment conditions
PROC8b Transfer of substance or mixture (charging and discharging) at dedicated facilities
PROC9 Transfer of substance or mixture into small containers (dedicated filling line, including
weighing)
• Environmental release category
ERC4 Use of non-reactive processing aid at industrial site (no inclusion into or onto article)
ERC7 Use of functional fluid at industrial site
Description of the activities / processes covered in the Exposure Scenario
See section 1 of the annex to the Safety Data Sheet.
· Conditions of use
· Duration and frequency 5 workdays/week. · Physical parameters
· Physical parameters
 Physical state Fluid Concentration of the substance in the mixture The substance is main component
Concentration of the substance in the mixture The substance is main component.
• Other operational conditions
• Other operational conditions affecting environmental exposure No special measures required.
• Other operational conditions affecting consumer exposure Not required.
• Other operational conditions affecting consumer exposure during the use of the product
Not applicable.
· Risk management measures
Worker protection
 Organisational protective measures No special measures required. Technical protective measures No special measures required.
• Personal protective measures No special measures required.
• Measures for consumer protection No special measures required.
• Environmental protection measures
· Air No special measures required.
• Water No special measures required.
· Disposal measures
Disposal must be made according to official regulations.
Ensure that waste is collected and contained.
• Disposal procedures Dispose of product residues with household waste.
• Waste type Partially emptied and uncleaned packaging
· Exposure estimation
• Consumer Not relevant for this Exposure Scenario.
• Guidance for downstream users No further relevant information available.
Annex: Exposure scenario 2
· Short title of the exposure scenario
Professional use of lubricants and greases in vehicles or machines
· Sector of Use
SU22 Professional uses: Public domain (administration, education, entertainment, services,
craftsmen)
· Product category
PC16 Heat transfer fluids
PC17 Hydraulic fluids
PC24 Lubricants, greases, release products
(Contd. on page 12)

Page 12/13

Safety data sheet according to 1907/2006/EC, Article 31



Printing date 13.03.2023

Version number 2.1 (replaces version 2.0)

Trade name: KTM RACING 4T SAE 20W/60

(Contd. of page 11)
· Process category
PROC1 Chemical production or refinery in closed process without likelihood of exposure or
processes with equivalent containment conditions.
PROC2 Chemical production or refinery in closed continuous process with occasional controlled
exposure or processes with equivalent containment conditions
PROC8a Transfer of substance or mixture (charging and discharging) at non-dedicated facilities
PROC8b Transfer of substance or mixture (charging and discharging) at dedicated facilities
PROC20 Use of functional fluids in small devices
Environmental release category
ERC9a Widespread use of functional fluid (indoor)
ERC9b Widespread use of functional fluid (outdoor)
Description of the activities / processes covered in the Exposure Scenario
See section 1 of the annex to the Safety Data Sheet.
· Conditions of use
Duration and frequency 5 workdays/week.
· Physical parameters
• Physical state Fluid
• Concentration of the substance in the mixture The substance is main component.
· Other operational conditions
 Other operational conditions affecting environmental exposure No special measures required. Other operational conditions affecting consumer exposure Not required.
• Other operational conditions affecting consumer exposure during the use of the product
Not applicable.
· Risk management measures
· Worker protection
· Organisational protective measures No special measures required.
• Technical protective measures No special measures required.
· Personal protective measures No special measures required.
• Measures for consumer protection No special measures required.
• Environmental protection measures
• Air No special measures required.
· Water No special measures required.
· Disposal measures
Disposal must be made according to official regulations.
Ensure that waste is collected and contained.
 Disposal procedures Dispose of product residues with household waste.
Waste type Partially emptied and uncleaned packaging
Exposure estimation
Consumer Not relevant for this Exposure Scenario.
Guidance for downstream users No further relevant information available.
Annovi Evnoquito oconorio 2
Annex: Exposure scenario 3
· Short title of the exposure scenario Private use of lubricants and greases in vehicles or machines
· Sector of Use SU21 Consumer uses: Private households / general public / consumers
 Product category PC24 Lubricants, greases, release products
Environmental release category
ERC9a Widespread use of functional fluid (indoor)
ERC9b Widespread use of functional fluid (outdoor)
 Description of the activities / processes covered in the Exposure Scenario
See section 1 of the annex to the Safety Data Sheet.
· Conditions of use
 Duration and frequency 5 workdays/week.

- Physical parameters
- · Physical state Fluid
- · Concentration of the substance in the mixture The substance is main component.

(Contd. on page 13)

⁻ GB -



Printing date 13.03.2023

Version number 2.1 (replaces version 2.0)

Other operational conditions	(Contd. of page
Other operational conditions affecting environmental expe	
Other operational conditions affecting consumer exposure	
Other operational conditions affecting consumer exposure	e during the use of the product
Not applicable.	
Risk management measures	
Worker protection	
Organisational protective measures No special measures re	
Technical protective measures No special measures require	
Personal protective measures No special measures required	
Measures for consumer protection No special measures red	quirea.
Environmental protection measures	
Air No special measures required.	
Water No special measures required. Disposal measures	
Disposal measures Disposal must be made according to official regulations.	
Ensure that waste is collected and contained.	
Disposal procedures Dispose of product residues with house	phold waste
Waste type Partially emptied and uncleaned packaging	shou waste.
Exposure estimation	
Consumer Not relevant for this Exposure Scenario.	
Guidance for downstream users No further relevant informa	ntion available